




nuh yapı ürünleri a.ş.



QUALITY –ENVIRONMENT
AND MANAGEMENT
SYSTEMS

HYDRATED LIME (CL 80 S) (TS EN 459-1)

Chemical analysis	%Constituents	TS EN 459-1
Ca(OH) ₂	: min. 80	
CaO + MgO	: min. 88	min. 80
MgO	: max. 3	max. 5
SO ₃	: max. 2	max. 2
Loss on ignition	: max. 7	max. 7
Moisture	: max. 1	max. 2

Physical analysis	% Finess	TS EN 459-1
Residue on 200µ	: max. 1	max. 2
Residue on 90µ	: max. 6	max. 7
Bulk density (kg/dm ³)	: max. 0,5	max. 0,6

- In accordance to TS EN 459-2 standart
- Nuh Yapı Ürünleri A.Ş. can not be reproduced without permission

QUALITY –ENVIRONMENT AND
MANAGEMENT SYSTEMS MANAGER